

FREP

HDPE

DMDA8008

Product information

Manufacturer Fujian Refining & Petrochemical Company Limited

Color NC

Material Shape Pellets

Process Injection molding

Material Attribute Injection grade

Mechanical behavior	Condition	Standard	Value	Unit
Elongation	Break	GB/T 1040	200	%
Tensile	Strength Yield	GB/T 1040	25	MPa
Physical property	Condition	Standard	Value	Unit
Density		GB/T 1033	0.956	g/cm ³
Melt	Index	GB/T 3682	7.5	g/10min
Thermal	Condition	Standard	Value	Unit
Vicat	Softening Temperature	GB/T 1633	-60	°C